

## WHALEBONE PLANK FLOORS PRODUCT INFORMATION

### PRODUCT DESCRIPTION

Junckers solid hardwood whalebone planks are produced in short lengths making them suitable for pattern floor installations, e.g. herringbone.

The planks are made as one whole floor board, tongued and grooved on all four sides. The planks are available as right- and left hand staves.

### PRODUCT DATA / TOLERANCES

#### Nominal Board Dimensions:

Thickness x width x length

- 20.5 x 140.0 x 701 mm

- 20.5 x 185.0 x 741 mm

- 15.0 x 129.0 x 775 mm

#### Tolerances:

Thickness: ( $\pm 0.2$  mm)

Width: ( $\pm 0.2$  mm)

Length: ( $\pm 0.2$  mm).

#### Drying Method:

The floor boards are kiln dried.

#### Moisture Content:

Oak: 8% ( $\pm 2\%$ ).

Black Oak: 9% ( $\pm 2\%$ ).

#### Precision Engineering:

Landing Deviation: 0.2 mm

(0.3 mm in localised areas).

Floors board ends are right angled at

$\pm 0.3$  mm.

### PRODUCT RANGE

Wood Species / Product name	Grade	Surface
Oak	Harmony	Ultra matt lacquered Silk matt lacquered Oiled Untreated Coloured* Textured* Textured & coloured*
Black Oak	Harmony	Ultra matt lacquered Oiled Untreated Textured* Textured & coloured*

\*According to standard product range

## TECHNICAL PROPERTIES

### Resistance to Indentation

All Oak products: Approx. 3.4 Hardness Brinell

### Slip Resistance, (preliminary):

Factory lacquered and oiled: Approx. 0.4 (DIN 18032/2)

### Fire Classification, (DIN EN 13501-1): C<sub>fl</sub> – S<sub>1</sub>

### Thermal Conduction, (Transmission coefficient):

Approx. 0.17 W/mK

### Heat Resistance:

20.5 x 140.0 x 701 mm: Approx. 0.12 m<sup>2</sup> K/W

20.5 x 185.0 x 701 mm: Approx. 0.12 m<sup>2</sup> K/W

15.0 x 129.0 x 775 mm: Approx. 0.09 m<sup>2</sup> K/W

## FACTORY SURFACE TREATMENT

### Lacquered

Oak:

Priming: Several coats of UV-light curing primer.

Top finish: Two-component polyurethane lacquer, silk- or ultra matt.

Total film thickness: Min. 40 µ.

Black Oak:

Pre-treatment: NH<sub>3</sub>-treatment to achieve the dark colour.

Intermediate treatment: Several coats of UV-light curing lacquer.

Top finish: Two-component polyurethane lacquer, ultra matt.

Total film thickness: Min. 40 µ.

### Oiled

Priming: Surface saturation using oxidative drying urethane oil.

Top finish: Oxidative drying urethane oil.

Total oil consumption: Addition to a full surface saturation.

### Untreated

Final sanding to grit 150.

## PACKING AND WEIGHT

Wrapped in polythene.

### 20.5 x 140.0 x 701 mm

Packsize: 12 boards (1.18 m<sup>2</sup>)

Weight per pack: 17.3 kg (14.7 kg/m<sup>2</sup>)

### 20.5 x 185.0 x 741 mm

Packsize: 8 boards (1.10 m<sup>2</sup>)

Weight per pack: 16.2 kg (14.7 kg/m<sup>2</sup>)

### 15.0 x 129.0 x 775 mm

Packsize: 16 boards (1.60 m<sup>2</sup>)

Weight per pack: 19.20 kg (12.0 kg/m<sup>2</sup>)